

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>B29C 70/50, F41H 1/02, B32B 5/12</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 97/00766</b> <b>(43) International Publication Date:</b> 9 January 1997 (09.01.97)
<b>(21) International Application Number:</b> PCT/NL96/00247 <b>(22) International Filing Date:</b> 14 June 1996 (14.06.96)  <b>(30) Priority Data:</b> 1000598 20 June 1995 (20.06.95) NL  <b>(71) Applicant (for all designated States except US):</b> DSM N.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).  <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> VAN DER LOO, Leonardus, Lambertus, Henricus [NL/NL]; Iepenlaan 7, NL-6176 DK Spaubeek (NL).  <b>(74) Agent:</b> DERKS, Wilhelmus, Hubertus, Petrus; Octrooibureau DSM, P.O. Box 9, NL-6160 MA Geleen (NL).		<b>(81) Designated States:</b> CA, IL, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i> <i>In English translation (filed in Dutch).</i>
<b>(54) Title:</b> BALLISTIC-RESISTANT MOULDED ARTICLE AND A PROCESS FOR THE MANUFACTURE OF THE MOULDED ARTICLE  <b>(57) Abstract</b>  The invention relates to a ballistic-resistant moulded article containing a compressed stack of monolayers, with each monolayer containing unidirectionally oriented reinforcing fibres and at most 30 wt.% of a plastic matrix material and with the fibre direction in each monolayer being rotated with respect to the fibre direction in an adjacent monolayer, characterized in that the density ( $\rho_P$ ) of the compressed stack is at least 98.0 % of the theoretical maximum density. The invention also relates to a process for manufacturing the moulded article. The ballistic-resistant article may be used in, for instance, helmets, as inserts in bullet-proof vests, as armouring on military vehicles and in ballistic-resistant panels.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

- 1 -

5     BALLISTIC-RESISTANT MOULDED ARTICLE AND A PROCESS FOR  
          THE MANUFACTURE OF THE MOULDED ARTICLE

          The invention relates to a ballistic-  
10    resistant moulded article containing a compressed stack  
      of monolayers, with each monolayer containing  
      unidirectionally oriented reinforcing fibres and at  
      most 30 wt.% of a plastic matrix material and with the  
      fibre direction in each monolayer being rotated with  
15    respect to the fibre direction in an adjacent  
      monolayer. The invention also relates to a process for  
      the manufacture of the moulded article. The ballistic-  
      resistant moulded article may be used in, for instance,  
      helmets, as inserts in bullet-proof vests, as armouring  
20    on military vehicles and in ballistic-resistant panels.

          A ballistic-resistant moulded article of this  
      type is disclosed in WO 89/06190. The known ballistic-  
      resistant moulded article affords fairly good  
      protection against impacts of projectiles such as  
25    shrapnel or bullets. The level of protection is  
      quantified by means of the Specific Energy Absorption  
      (SEA), a measure of the amount of energy that can be  
      absorbed by a moulded article on impact of a projectile  
      per unit areal density of the moulded article. Fairly  
30    good protection by the known moulded article on impact  
      of a bullet is intended to mean an SEA value of from  
      about 30 Jm<sup>2</sup>/kg to maximum 65 Jm<sup>2</sup>/kg. The March 1992  
      "Ballistics" leaflet of Messrs Allied-Signal Inc.,  
      Petersburg, Virginia, quotes as highest SEA level an  
35    SEA of 65 Jm<sup>2</sup>/kg on impact of a 7.62 x 39 Mild Steel  
      Core P.S. Ball M1943. This SEA level has been achieved  
      after years of optimization and was regarded by  
      ballistics experts as being very high.

Nevertheless, there continues to be a great need for ballistic-resistant moulded articles that can offer increased protection against impacts of projectiles of various kinds, especially against  
5 projectiles in the form of bullets.

The inventors of the present invention have found that this object is achieved by the density  $\rho_p$  of the compressed stack in the ballistic-resistant moulded article being at least 98.0% of the theoretical maximum  
10 density.

The theoretical maximum density  $\rho_{th}$  is calculated using the following formula:

$$\rho_{th} = \rho_f m_f + \rho_k m_k$$

where

15  $\rho_f$  = density of the fibres

$\rho_k$  = density of the plastic

$m_f$  = mass fraction of the fibres in the compressed stack

20  $m_k$  = mass fraction of the plastic in the compressed stack

Surprisingly, a ballistic-resistant moulded article of the invention has an SEA value of at least 75 Jm<sup>2</sup>/kg on impact of a 7.62 x 39 Mild Steel Core P.S.  
25 Ball M1943.

The percentage of the theoretical maximum density is hereafter referred to as the relative density. Preferably, the relative density of the compressed stack is at least 98.5%, more preferably at  
30 least 99.0% and most preferably at least 99.5%. In this way, a ballistic-resistant moulded article having an even better SEA value is obtained. More preferably, the SEA value is at least 90, even more preferably at least 110 Jm<sup>2</sup>/kg, most preferably at least 120 Jm<sup>2</sup>/kg.

35 The density of the ballistic-resistant moulded article can be determined in a manner known to one skilled in the art. A suitable, accurate method is

described in ASTM D 792-91. Another suitable method for flat or slightly flexed moulded articles comprises measurement of the density by measuring the weight and accurately measuring the volume with the aid of a Vernier calliper. By this measurement, if accurately performed, the density can be determined with a standard deviation of 0.2-0.4%.

The SEA is defined by  $0.5 \cdot m \cdot v_{50}^2 / AD$ , where  $m$  is the mass of the projectile. The  $v_{50}$  is the velocity of the projectiles fired at the moulded article at which 50% of the projectiles fully penetrate the moulded article,  $AD$  is the areal density of the moulded article.

Owing to the surprisingly high SEA achieved, not only moulded articles with an unheard-of level of protection for a given weight of the moulded article are now available but also moulded articles affording the same level of protection as the known moulded article at a significantly lower weight. Low weight per unit area is of great importance in many applications. This is the case, for instance, in the field of personal protective equipment such as helmets, shields, shoes and the like. Low weight is also essential for the application of ballistic-resistant moulded articles in for instance helicopters, motorcars and high-speed, highly manoeuvrable combat vehicles.

The areal density of the moulded article depends on the desired level of protection. Preferably, the areal density is between 10 and 40 kg/m<sup>2</sup>. Below 10 kg/m<sup>2</sup>, the level of protection is inadequate for most threats, above 40 kg/m<sup>2</sup> the weight will often be too high, especially for body protection.

In the context of the present application "monolayer" means a layer of substantially parallel reinforcing fibres embedded in a plastic matrix material. The term "matrix material" means a material which binds the fibres together and which wholly or

partially encapsulates the fibres. Such monolayers (usually called prepregs by one skilled in the art) and methods of obtaining such a monolayer are disclosed in for instance EP-B-0.191.306 and WO 95/00318. A

5 monolayer may be obtained by for instance pulling a number of fibres from a fibre bobbin frame over a comb so that they are oriented in coplanar and parallel fashion in one plane and then impregnating the fibres with the plastic. In this process, fibres may be used

10 that have previously been coated with a polymer other than the plastic matrix material in order to, for instance, protect the fibres during handling or in order to obtain better adhesion of the fibres onto the plastic of the monolayer. Preferably, uncoated fibres

15 are used. Impregnation of the reinforcing fibres with the plastic matrix material can be effected by applying one or more films of the plastic to the top, bottom or both sides of the plane of the fibres and then passing these, together with the fibres, through a heated

20 pressure roll. Preferably, however, the fibres, after being oriented in coplanar, parallel fashion in one plane, are coated with an amount of a liquid substance containing the plastic matrix material of the monolayer. The advantage of this is that more rapid and

25 better impregnation of the fibres is achieved. The liquid substance may be for example a solution, a dispersion or a melt of the plastic. If a solution or a dispersion of the plastic is used in the manufacture of the monolayer, the process also comprises evaporating

30 the solvent or dispersant.

"Reinforcing fibre" here means an elongate body whose length dimension is greater than the transverse dimensions of width and thickness. The term "reinforcing fibre" includes a monofilament, a

35 multifilament yarn, a tape, a strip, a thread, a staple fibre yarn and other elongate objects having a regular or irregular cross-section. Any natural or synthetic

fibre may in principle be used as reinforcing fibre. Use may be made of for instance metal fibres, semi-metal fibres, inorganic fibres, organic fibres or mixtures thereof. For application of the fibres in  
5 ballistic-resistant moulded parts it is essential that the fibres be ballistically effective, which, more specifically, requires that they have a high tensile strength, a high tensile modulus and/or high energy  
10 absorption. It is preferred for the fibres to have a tensile strength of at least 1.2 GPa and a tensile modulus of at least 40 GPa.

Suitable inorganic fibres having a high tensile strength are for example glass fibres, carbon fibres and ceramic fibres. Suitable organic fibres  
15 having a high tensile strength are for example aramid fibres, liquid crystalline polymer fibres and fibres of for instance polyolefins, polyvinylalcohol, polyacrylonitrile which are highly oriented such as those obtained by means of a gel spinning process.

20 An extensive enumeration and description of fibres that may be used in the monolayer are given in WO 91/12136 (line 23 on page 6 to line 8 on page 12).

Homopolymers and copolymers of polyethylene and polypropylene are particularly suitable as  
25 polyolefins. Furthermore, the polyolefins used may contain small amounts of one or more other polymers, in particular other alkene-1-polymers.

It is preferred for the reinforcing fibres in the monolayer to be high-drawn fibres of high-molecular  
30 weight linear polyethylene. High molecular weight here means a molecular weight of at least 400,000 g/mol.

Linear polyethylene here means polyethylene having fewer than 1 side chain per 100 C atoms, preferably fewer than 1 side chain per 300 C atoms. The  
35 polyethylene may also contain up to 5 mol % of one or more other alkenes which are copolymerisable therewith, such as propylene, butene, pentene, 4-methylpentene,

octene.

Preferably, use is made of polyethylene fibres consisting of polyethylene filaments prepared by a gel spinning process as described in for example GB-A-2042414 and GB-A-2051667. This process essentially comprises the preparation of a solution of a polyolefin of high intrinsic viscosity, spinning the solution to filaments at a temperature above the dissolving temperature, cooling down the filaments below the gelling temperature so that gelling occurs and drawing the filaments before, during or after removal of the solvent.

The shape of the cross-section of the filaments can be selected here through selection of the shape of the spinning aperture.

Preferably, the monolayer contains reinforcing fibres, preferably the aforementioned strong polyethylene fibres, with a denier per filament (dpf) greater than or equal to 1.5. Most preferably, use is made of multifilament yarns of ultrahigh molecular weight linear polyethylene with an intrinsic viscosity of at least 5 dl/g, determined in decalin at 135°C, and a yarn titre of at least 50 denier, with the yarn having a tensile strength of at least 35 cN/dtex and a tensile modulus of at least 1000 cN/dtex and the filaments having a cross-section aspect ratio of at most 3. The use of these fibres has been found to improve the high level of protection of the ballistic-resistant panel of the invention still further.

The plastic matrix material may wholly or partially consist of a polymer material, which optionally may contain fillers usually employed for polymers. The polymer may be a thermoset or thermoplastic or mixtures of both. Preferably a soft plastic is used, in particular it is preferred for the plastic matrix material to be an elastomer with a tensile modulus (at 25°C) of at most 41 MPa.



Preferably, the elongation to break of the plastic is greater than the elongation to break of the reinforcing fibres. The elongation to break of the matrix preferably is from 3 to 500%.

5           Thermosets and thermoplastics that are suitable for the monolayer are listed in for instance WO-A-91/12136 (line 26, page 15 to line 23, page 21). Preferably, vinylesters, unsaturated polyesters, epoxides or phenol resins are chosen as matrix material  
10 from the group of thermosetting polymers. These thermosets usually are in the monolayer in partially set condition (the so-called B stage) before the stack of monolayers is cured during compression of the ballistic-resistant moulded article. From the group of  
15 thermoplastic polymers polyurethanes, polyvinyls, polyacryls, polyolefins or thermoplastic, elastomeric block copolymers such as polyisoprene-polyethylene-butylene-polystyrene or polystyrene-polyisoprene-polystyrene block copolymers are preferably chosen as  
20 matrix material.

          The plastic-matrix-material content of the monolayer is chosen sufficiently low, in any case lower than 30 wt.% relative to the total weight of the monolayer. Preferably, the content is lower than 20  
25 wt.%, most preferably lower than 10 wt.%.

          The fibre direction in each monolayer in the ballistic-resistant moulded article of the invention is rotated with respect to the fibre direction in an adjacent monolayer. This construction is hereafter  
30 referred to as being "cross-layered". Good results are achieved when this rotation amounts to at least 45 degrees. Preferably, this rotation amounts to approximately 90 degrees.

          The relatively high density and an SEA value  
35 of at least 75 Jm<sup>2</sup>/kg of the compressed stack of the invention can be achieved by taking a number of measures. It is possible for instance to ensure in a

number of stages in the manufacture of the moulded articles that as few low-density components, like air or from the polymer evaporated gasses as possible remain in the moulded article. This can for instance be accomplished by using a plastic of very low viscosity in impregnating the reinforcing fibres in the manufacture of the monolayer. It is also advantageous to spread the reinforcing fibres well during the impregnation process or to subject them to for instance ultrasonic vibration. As mentioned above, if multifilament yarns are used, it is important for a good spread that the yarns have a low twist. Furthermore, the plastic may be applied in vacuo. Each of these measures has a beneficial effect on the level of protection of a ballistic-resistant moulded article obtained with the monolayers but the level of protection of the moulded article of the invention is not attained or is attained only with great effort.

The invention also relates to a process for the manufacture of a ballistic-resistant moulded article in which monolayers are stacked cross-wise, whereupon the stack is compressed at a given pressure at an elevated temperature.

A process of this kind is disclosed in for instance WO 89/06190. It teaches that when the plastic matrix material is heated to its melting point, relatively low pressures are sufficient for shaping the moulded article. The pressures stated vary from 0.05 MPa to a maximum of 3 MPa.

It has now surprisingly been found that significantly higher SEA values than hitherto known in the state of the art can be attained by compressing and cooling the stack at a pressure of at least 5 MPa.

The pressure preferably is at least 7 MPa. In this way, the theoretical maximum density of the compressed stack is approached more closely and the level of protection against the impact of projectiles

is increased further. The pressure preferably is at least 10 MPa, more preferably at least 13 MPa and most preferably at least 15 MPa. Preferably, the pressures during compression at an elevated temperature and  
5 during cooling are the same.

Compression at an elevated temperature is intended to mean that the moulded article is subjected to the given pressure for a particular compression time at a compression temperature above the softening or  
10 melting point of the plastic matrix material and below the softening or melting point of the fibres. The required compression time and compression temperature depend on the kind of fibre and matrix material and on the thickness of the moulded article and can be readily  
15 determined by one skilled in the art.

It has been found that in order for a high SEA value to be attained it is necessary that after compression at an elevated temperature cooling, too, take place under pressure.  
20 Cooling under pressure is intended to mean that the given minimum pressure is maintained during cooling at least until so low a temperature is reached that the structure of the moulded article can no longer relax under atmospheric pressure so that the SEA value cannot  
25 decrease. This temperature is easy to establish by one skilled in the art. It is preferred for cooling at the given minimum pressure to be down to a temperature at which the plastic matrix material has largely or completely hardened or crystallized and below the  
30 relaxation temperature of the reinforcing fibres. The pressure during the cooling does not need to be equal to the pressure at the high temperature, but it is preferred that these pressures are equal. The pressure loss resulting from shrinkage of the moulded article  
35 and the pressure due to cooling must regularly be compensated for so as to keep the pressure during cooling constant or at least on a sufficient high

level.

As the stack of monolayers is heated to the desired compression temperature, the pressure preferably is increased to the desired level in, preferably at least three, discontinuous steps. In this way, blisters are prevented from forming.

For the manufacture of a ballistic-resistant moulded article in which the reinforcing fibres in the monolayer are high-drawn fibres of high-molecular-weight linear polyethylene, the compression temperature is preferably 115 to 130°C and cooling to below 70°C is effected at a constant pressure. Compression temperature here means the temperature at half the thickness of the moulded article.

In the process of the invention the stack may be made starting from loose monolayers. Loose monolayers are difficult to handle, however, in that they easily tear in the fibre direction. It is therefore preferred to make the stack from consolidated monolayer packages containing from 2 to 8, as a rule 2, 4 or 8, monolayers that are placed cross-wise. Consolidated is intended to mean that the monolayers are firmly attached to one another. Very good results are achieved if the monolayer packages, too, are compressed at an elevated temperature and cooled at a high pressure, preferably of at least 5 MPa.

In another embodiment of the process of the invention the ballistic-resistant moulded article is manufactured by a process whereby, in a first step, a semi-manufactured article is produced by forming a stack of cross-layered monolayers, which stack has an areal density of from 0.25 to 5 kg/m<sup>2</sup> and subsequently compressing this stack at an elevated temperature and cooling this stack at a given first pressure whereupon, in a second step, the semi-manufactured articles are compressed onto each other at an elevated temperature and cooled at a given second pressure, with the first

pressure being at least 5 MPa.

An advantage of this process is that, if the semi-manufactured articles are also compressed and cooled at a pressure of at least 5 MPa in the second step, the moulded articles obtained have a higher SEA value than moulded articles manufactured in a single compression step at the same pressure.

Another important advantage of the above-mentioned process is that high SEA values are attainable when the second pressure is relatively low, preferably at most 5 MPa. It has been found that good SEA values can be attained if the second pressure is lower than 5 MPa or even 3 MPa. A major advantage of this is that manufacturers of ballistic-resistant moulded articles, who often do not have high pressure moulds (i.e. higher than 5 MPa) at their disposal, can still achieve the good properties of the ballistic-resistant moulded article of the invention using conventional moulding equipment.

The semi-manufactured articles can then be centrally produced in locations where a high-pressure mould is available, for example at the manufacturer of the monolayers or monolayer packages.

The invention also relates to the semi-manufactured article for the manufacture of a ballistic-resistant moulded article of the invention that is obtainable by the first step in the above-mentioned process.

The semi-manufactured article has an areal density of from 0.25 to 5 kg/m<sup>2</sup>. An areal density lower than 0.25 kg/m<sup>2</sup> has the disadvantage that the SEA value of the ballistic-resistant moulded article ultimately obtained is lower. An areal density higher than 5 kg/m<sup>2</sup> has the disadvantage that there is little flexibility in the choice of the areal density of the ballistic-resistant moulded article ultimately to be formed and that the cycle time for compressing the semi-

manufactured article becomes unacceptably long. Preferably, the areal density of the semi-manufactured article is between 0.5 and 2.5 kg/m<sup>2</sup>.

It has surprisingly been found that, using  
5 the process of the invention, higher SEA values are attainable if the reinforcing fibres in the monolayers have a cross-section aspect ratio of at most 3. Cross-section aspect ratio is intended to mean the ratio of  
10 the longest to the shortest principal axis of a perpendicular cross-section of the fibre. Preferably, the aspect ratio is lower than 2, more preferably lower than 1.5. It has been found that high SEA values are obtained at low compressive pressures in ballistic-resistant moulded articles in which the filaments have  
15 a lower aspect ratio (being rounder). For the same reason, the filaments preferably also have a fineness of 1.5 denier per filament or more.

Furthermore, it has been found that, using  
20 the process of the invention, higher SEA values are attainable at comparable compressive pressures if the monolayers employed in the ballistic-resistant moulded article are obtained by impregnating reinforcing fibres with an aqueous dispersion which contains the plastic matrix material.

25 Furthermore, it has been found that, using the process of the invention, higher SEA values are attainable at comparable compressive pressures if the monolayers employed in the ballistic-resistant moulded article have a fibre weight higher than 25, more  
30 preferably higher than 50 g/m<sup>2</sup>. Preferably, the fibre weight is at most 150 g/m<sup>2</sup>, more preferably lower than 100 g/m<sup>2</sup>.

The invention is illustrated by means of the  
35 following examples without being limited thereto.

Examples I and II and comparative experiments A and B

Material used:

A monolayer package consisting of four monolayers disposed cross-wise at an angle of 90 degrees. The fibres are high-drawn fibres of high molecular weight linear polyethylene of make Dyneema SK66 (TM) with a strength of 32.5 cN/dtex, a modulus of 1015 cN/dtex and a fineness of 1 denier per filament with a cross-section aspect ratio of about 5. The monolayer contains 20 wt.% matrix material consisting of Kraton (TM) applied from an aqueous dispersion. Kraton is a styrene-isoprene-styrene triblock copolymer. The areal density of the monolayer package is 135 g/m<sup>2</sup>.

15 Procedure:

A number of the above-mentioned monolayer packages were stacked to yield a package whereupon the package in its entirety was placed between two platens of a standard press. The temperature of the platens was about 125-130°C. The package was retained in the press until the temperature at the centre of the package was 115-125°C. Subsequently, the pressure was increased to a compressive pressure as stated in Table 1 below and the package was kept under this pressure for 15 min. Next, the package was cooled to a temperature of 60°C at the same compressive pressure.

Test procedure:

The panels obtained were fired at in accordance with the procedure set out in STANAG 2920. Use was made of a 7.62 x 39 mm Mild Steel Core (PS Ball M 1943) bullet weighing 8 grammes. The bullet used had been obtained from Messrs Sellier & Bellot, Czech Republic. The experimental density of the panels was determined by accurate weighing and measurement of the volume using a Vernier calliper. The standard deviation according to this density measurement is 0.002-0.004

g/cm<sup>3</sup>.

### Results:

The  $v_{50}$  and SEA values as a function of the compressive pressure are given in Table 1. The stated SEA value was calculated from the total areal density of the ballistic-resistant moulded article. Relative density is intended to mean the ratio of the experimental density of the panel  $\rho_p$  and the theoretical density of the panel, which is defined by  $(\rho_f m_f + \rho_k m_k)$ . The theoretical density of the ballistic-resistant moulded article as calculated from  $\rho_f = 0.97$ ,  $m_f = 0.8$  and  $\rho_k = 0.943$  amounts to 0.965.

Table 1

	AD (kg/m <sup>2</sup> )	compressiv e pressure (MPa)	$V_{50}$ (m/sec)	SEA (Jm <sup>2</sup> /kg)	Relative density
A	33.5	1.0	591	42	0.969
B	33.5	2.5	668	53	0.974
I	33.8	7.0	825	81	0.990
II	26.9	16.5	772	89	0.992

The results indicate that, at equal areal density, the ballistic-resistant panel of the invention has a surprisingly higher SEA value than a panel with a lower rel. density. The table also shows that the panel of the invention can be obtained by choosing a compressive pressure of at least 5 MPa.



Examples III-VIMaterial used:

A monolayer package consisting of four  
5 monolayers disposed cross-wise at an angle of 90  
degrees. The monolayer package differs from the  
monolayer packages referred to in Examples I and II  
only in respect of the fibres used. The fibres are  
high-drawn fibres of high molecular weight linear  
10 polyethylene with a yarn titre of 880 denier, a tensile  
strength of 37.3 cN/dtex, a tensile modulus of 1220  
cN/dtex, an elongation to break of 3.7%, a fineness of  
2 denier per filament and a round cross-section aspect  
ratio of about 1. The monolayer contains 20 wt.% matrix  
15 material consisting of Kraton (TM). The areal density  
of the monolayer package is 135 g/m<sup>2</sup>.

Procedure and testing

Starting from the above-mentioned monolayer packages,  
20 ballistic-resistant moulded articles were produced at  
various compressive pressures and tested in the manner  
set out in Example 1. The ballistic-resistant panel  
obtained had an areal density equal to 25.9 kg/m<sup>2</sup> for  
all compressive pressures.

25

The results are given in Table 2.

Table 2

30

Example	compressive pressure (MPa)	V <sub>50</sub> (m/sec)	SEA Jm <sup>2</sup> /kg)	relative density (-)
III	1.0	741	85	0.981
IV	2.5	768	91	0.988
V	7.0	913	129	0.996

Example	compressive pressure (MPa)	$V_{50}$ (m/sec)	SEA $\text{Jm}^2/\text{kg}$	relative density (-)
VI	16.5	939	136	0.995

### Comparative Experiment C and Examples VII and VIII

5

In Comparative Experiment C and Examples VII and VIII, ballistic-resistant moulded articles were produced from monolayer packages as described in Example I in the manner described above. The compressive pressures in Comparative Experiment C and Example VII were 1 MPa and 7 MPa, respectively. In Example VIII, semi-manufactured articles consisting of 5 monolayer packages were first moulded at a first compressive pressure of 5 MPa, which semi-manufactured articles were then stacked and compressed at a second pressure of 1 MPa. In each case, the compressive pressure was kept at the same level during cooling. The results are given in Table 3.

Table 3

20

	AD $(\text{kg}/\text{m}^2)$	compressive pressure (MPa)	$V_{50}$ (m/sec)	SEA $(\text{Jm}^2/\text{kg})$
C	29.6	1	614	51
VII	33.8	7	825	81
VIII	29.1	5/1	739	75

25

### Comparative Experiments D and E and Examples IX and X

As the first starting material (S1) a monolayer package available under the name of SpectraShield (TM) and consisting of four monolayers

disposed crosswise at an angle of 90 degrees. The fibres are high-drawn fibres of high-molecular-weight linear polyethylene of make Spectra 1000 (TM) with a fineness of 5.5 denier per filament and a cross-section aspect ratio of about 1. The monolayer was obtained by  
5 impregnating the unidirectional fibres with a solution of the matrix material Kraton (TM).

As the second starting material (S2) a  
10 monolayer package was prepared by first preparing a monolayer starting from Spectra 1000 fibres which were impregnated with an aqueous dispersion (instead of a solution as in S1) of the matrix material Kraton. The yarn weight in the monolayer is 52 g/m<sup>2</sup>, the matrix  
15 content is 20%. Of these monolayers four-layer monolayer packages were made.

The monolayer packages S1 and S2 were stacked and compressed into ballistic-resistant moulded  
20 articles as described above. In Comparative Experiment D and Example IX starting material S1 was used, in Comparative Experiment E and Example X starting material S2 was used. The compressive pressures used and the results are given in Table 4.

25

Table 4

30

Example	AD (kg/m <sup>2</sup> )	compressive pressure (MPa)	V <sub>50</sub> (m/sec)	SEA (Jm <sup>2</sup> /kg)
D (S1)	24.9	1	524	44
E (S2)	22	1	598	65
IX (S1)	24.9	5	761	93
X (S2)	22	5	792	114

A comparison between Comparative Experiments D and E and Examples IX and X shows the great improvement in ballistic resistance. A comparison of the starting materials S1 and S2 in Examples VII and VIII shows the  
5 great improvement in ballistic resistance obtained when the monolayers have been prepared with an aqueous dispersion of the matrix material in combination with high-pressure compression.

C L A I M S

1. Ballistic-resistant moulded article containing a  
5 compressed stack of monolayers, with each  
monolayer containing unidirectionally oriented  
reinforcing fibres and at most 30 wt.% of a  
plastic matrix material and with the fibre  
10 direction in each monolayer being rotated with  
respect to the fibre direction in an adjacent  
monolayer, characterized in that the density ( $\rho_P$ )  
of the compressed stack is at least 98.0% of the  
theoretical maximum density.
2. Ballistic-resistant moulded article according to  
15 claim 1, characterized in that the density  $\rho_P$  is  
at least 99.0% of the theoretical maximum density.
3. Ballistic-resistant moulded article according  
to claim 1 or claim 2, characterized in that  
the reinforcing fibres in the monolayer have  
20 a tensile strength of at least 1.2 GPa and a  
tensile modulus of at least 40 GPa.
4. Ballistic-resistant moulded article according to  
any one of the claims 1-3, characterized in that  
the reinforcing fibres in the monolayer are high-  
25 drawn fibres of high-molecular-weight linear  
polyethylene.
5. Ballistic-resistant moulded article according to  
claim 1, characterized in that the plastic matrix  
material is an elastomer with a tensile modulus  
30 (at 25°C) of at most 41 MPa.
6. Ballistic-resistant moulded article according to  
claim 1, characterized in that the rotation  
amounts to 90 degrees.
7. Process for manufacturing a ballistic-resistant  
35 moulded article in which a stack is made of  
crosswise-arranged monolayers, upon which the  
stack is compressed at an elevated temperature,

characterized in that the stack is compressed and cooled at a pressure of at least 5 MPa.

8. Process for manufacturing a ballistic-resistant moulded article in which in a first step a semi-manufactured article is produced by forming a stack of cross-layered monolayers, which stack has an areal density of from 0.25 to 5 kg/m<sup>2</sup>, and subsequently compressing this stack at an elevated temperature and cooling this stack at a given first compressive pressure whereupon, in a second step, the semi-manufactured articles are compressed onto each other at an elevated temperature and cooled at a given second pressure, with the first pressure being at least 5 MPa.
9. Process according to claim 8, characterized in that the second pressure is at most 5 MPa.
10. Process according to claim 7 or 8, characterized in that the stack is made from consolidated monolayer packages containing from 2 to 8 monolayers that are placed cross-wise.
11. Process according to claim 10, characterized in that the monolayer packages, too, are compressed and cooled at a pressure of at least 5 MPa.
12. Process according to any one of the claims 7, 8 or 11, characterized in that the specified pressure is at least 7 MPa.
13. Process according to any one of the claims 7, 8 or 11, characterized in that the specified pressure is at least 10 MPa.
14. Process according to any one of the claims 7-13, characterized in that the reinforcing fibres in the monolayers have a cross-section aspect ratio of at most 3.
15. Process according to any one of the claims 7-14, characterized in that the monolayer has been obtained by impregnating the reinforcing fibres with an aqueous dispersion containing the plastic

matrix material.

16. Process according to any one of the claims 7-15, characterized in that the monolayer has a fibre weight of between 50 and 150 g/m<sup>2</sup>.
- 5 17. Ballistic-resistant moulded article obtainable according to the process of any of the claims 7-16.
18. Semi-manufactured article according to the first step in the process according to claim 8 for the  
10 manufacture of a ballistic-resistant moulded article according to any one of the claims 8-15.
19. Ballistic-resistant moulded article according to claims 1-6 or 17, characterized in that the  
15 moulded article has a specific energy absorption (SEA) of at least 75 Jm<sup>2</sup>/kg on impact of a 7.62 x 39 Mild Steel Core P.S. Ball M1943 bullet.

# INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/NL 96/00247

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 B29C70/50 F41H1/02 B32B5/12

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 F41H B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,4 953 234 (H.I. LI ET AL) 4 September 1990 see column 4, line 61 - column 5, line 14	1-7, 15-17
A	see column 9, line 55 - column 10, line 2; claims 1,6-10,16-18; figures 5-8; examples 1,2	8-14,18, 19
A	--- WO,A,89 06190 (ALLIED-SIGNAL INC.) 13 July 1989 cited in the application see the whole document	1-19
A	--- GB,A,2 051 667 (STAMICARBON BV) 21 January 1981 cited in the application see figures 5,6 --- -/--	3,4

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*&\* document member of the same patent family

Date of the actual completion of the international search

4 September 1996

Date of mailing of the international search report

17.09.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Van Nieuwenhuize, 0



# INTERNATIONAL SEARCH REPORT

Int. Application No  
PCT/NL 96/00247

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,5 124 195 (GARY A. HARPELL ET AL) 23 June 1992 see column 9, line 32 - line 39 ---	1-7
A	US,A,3 743 561 (ROBERT D. KOONTZ ET AL) 3 July 1973 see column 5, line 33 - line 45; claim 1 -----	1,2

## INTERNATIONAL SEARCH REPORT

Inv. No. Application No  
PC 96/00247

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4953234	04-09-90	CA-A- 1311087 EP-A- 0380523 JP-T- 3501140 WO-A- 8901123 US-A- 5112667	08-12-92 08-08-90 14-03-91 09-02-89 12-05-92
WO-A-8906190	13-07-89	US-A- 4916000 DE-D- 3851844 DE-T- 3851844 EP-A- 0397696 JP-T- 3502431 US-A- 5160776	10-04-90 17-11-94 16-02-95 22-11-90 06-06-91 03-11-92
GB-A-2051667	21-01-81	NL-A- 7904990 AT-B- 382399 AU-B- 527155 AU-B- 5965480 BE-A- 884017 CA-A- 1147518 CH-A- 650807 DE-A- 3023726 FR-A- 2459845 JP-A- 63264911 JP-B- 1024887 JP-A- 56015408 JP-A- 63085107 JP-A- 63066316 SE-B- 443164 SE-A- 8004704 US-A- 4344908 US-A- 4422993 US-A- 4430383	30-12-80 25-02-87 17-02-83 08-01-81 29-12-80 07-06-83 15-08-85 15-01-81 16-01-81 01-11-88 15-05-89 14-02-81 15-04-88 25-03-88 17-02-86 28-12-80 17-08-82 27-12-83 07-02-84
US-A-5124195	23-06-92	NONE	
US-A-3743561	03-07-73	NONE	